AMENDMENTS TO THE CLAIMS:

This listing of claims will replace all prior versions, and listings, of claims in the application:

LISTING OF CLAIMS:

- 1-2. (Canceled)
- (Currently Amended) A solvent dispersion for a printing ink, wherein the a
 polyethylene-based wax-according to elaim 1 that is produced with a metallocene-based
 catalyst and is subjected to oxidative modification, and specified by the following (i) to (vii):
- (i) being an ethylene homopolymer or a copolymer of ethylene and at least one αolefin selected from α-olefins having 3 to 20 carbon atoms,
- (ii) having the intrinsic viscosity [n] determined in decalin at 135°C ranging from 0.06 to 0.35 dl/g.
- (iii) having the ratio (Mw/Mn) of weight average molecular weight (Mw) to number average molecular weight (Mn) determined by gel permeation chromatography (GPC) ranging from 1.7 to 3.2,
- (iv) having the ratio (Mz/Mw) of z-average molecular weight (Mz) to weight average molecular weight (Mw) determined by gel permeation chromatography (GPC) ranging from 1.5 to 2.0,
 - (v) having the density ranging from 920 to 980 kg/m³,
 - (vi) having the penetration hardness of 5 dmm or less, and
- (vii) having the acid value ranging from 0.3 to 9.9 KOH-mg/g, is dispersed in the form of fine particles having a volume average particle diameter ranging from 0.3 to 10 μm

Attorney Docket No. 1000023-000104 Application No. 10/573,840 Page 3

and at a ratio of 5 to 50 wt.% based on the total weight of the solvent dispersion in a nonaromatic solvent.

- 4. (Previously Presented) The solvent dispersion for a printing ink according to claim 3, wherein the non-aromatic solvent contains an alcohol-based solvent and/or an esterbased solvent at a ratio of 10 wt.% or more based on the total weight of the non-aromatic solvent.
- 5. (Currently Amended) A printing ink comprising the solvent dispersion according to claim 3, wherein in which the polyethylene-based wax according to claim 1-is contained in the form of fine particles having a volume average particle diameter ranging from 0.3 to 10 µm and at a ratio of 0.1 to 10 wt.%, and the content of an aromatic solvent is less than 5 wt.% based on the total weight of the printing ink composition.